
Technical Data Sheet

Isopropyl Alcohol 99.9% ACS Reagent Grade

ACS Reagent · 99.9% w/w

Alliance Code	Revised	Revision
isopropyl-alcohol-99-9-acs-reagent-grade	2026-10-13	1.5

CAS number 67-63-0	UN number UN1219	Hazard class · packing group 3 · PG II
 Structure · PubChem	Grade ACS Reagent · 99.9% w/w	Signal word **Danger**
Hazards Flammable · Irritant / harmful · H225 H319 H336		
Proper shipping name Isopropanol or isopropyl alcohol		

IDENTITY & COMPOSITION

PRODUCT NAME
Isopropyl Alcohol 99.9% ACS Reagent Grade

ALLIANCE CODE
isopropyl-alcohol-99-9-acs-reagent-grade

GRADE
ACS Reagent

CONCENTRATION
99.9% w/w

CAS NUMBER
67-63-0 PubChem

FORMULA
C3H8O PubChem

MOLECULAR WEIGHT
60.10 PubChem

PRODUCT TYPE
Solution

IUPAC NAME
propan-2-ol PubChem

INCHI-KEY
KFZMGEQAYNKOFK-UHFFFAOYSA-N PubChem

SMILES
CC(C)O PubChem

PHARMACOPOEIA COMPLIANCE: USP ACS

SPECIFICATIONS

TEST	SPECIFICATION	TYPICAL	METHOD	SOURCE
Assay (CH3CHOHCH3)	>= 99.5 % w/w	—	—	Interpreted
Titrable acid or base	max. 0.0001 meq/g	—	—	Interpreted
Titrable Base	<= 0.0001 meq/g	—	—	Interpreted
Carbonyl compounds (as acetone)	max. 0.002 %	—	—	Interpreted
Color (APHA)	<= 10	—	—	Interpreted
Residue after Evaporation	<= 0.001 %	—	—	Interpreted
Solubility in H2O	Passes Test	—	—	Interpreted
Water (H2O)	<= 0.2 %	—	Karl Fischer titrn	Interpreted
Substances darkened by sulfuric acid	Passes test	—	ACS monograph test - shake with H2SO4, compare acid layer	Interpreted
Identification (Infrared Absorption)	Conforms to structure	—	FTIR-ATR, comparison to reference spectrum	Interpreted
Distillation, dry point	82.8 °C max	—	—	Interpreted
Distillation, initial boiling point	81.8 °C min	—	—	Interpreted

Values are reproduced from the current product reference. Source labels do not by themselves establish a supplier guarantee or a test result for your lot. Confirm applicable acceptance limits and request lot-specific documentation.

AVAILABLE GRADES SAME CAS, ALTERNATE GRADES AND CONCENTRATIONS

GRADE	CONCENTRATION	TYPICAL ASSAY	SKU
THIS GRADE ACS Reagent	99.9% w/w	—	current
Technical	99% w/w	—	isopropyl-alcohol-99
USP Grade	91% v/v	—	isopropyl-alcohol-91
USP Grade	70% v/v	—	isopropyl-alcohol-70-usp-grade
Technical	60% v/v	—	isopropyl-alcohol-60-technical-grade
USP	60% v/v	—	isopropyl-alcohol-60-usp-grade
Technical	50% v/v	—	isopropyl-alcohol-50-technical-grade
USP	50% v/v	—	isopropyl-alcohol-50-usp-grade

Typical assay for each grade is the average of its recent lots. Confirm a grade meets your specification before substituting it.


PHYSICAL & CHEMICAL PROPERTIES

PROPERTY	VALUE	SOURCE
Appearance	Transparent, mobile liquid with high volatility	Adjudicated
Form	Liquid	Published reference
Odor	Alcohol-like odor	Adjudicated
Specific Gravity	0.785–0.787 at 20 °C (water = 1)	Adjudicated
Density	0.785 - 0.786 g/ml	Interpreted
Boiling Point	82–83 °C (180–181 °F) at 760 mmHg	Adjudicated
Melting Point	-89 °C (-128 °F)	Adjudicated
Flash Point	12 °C (54 °F), closed cup	Adjudicated
Vapor Pressure	33 mmHg (4.4 kPa) at 20 °C	Adjudicated
Vapor Density	2.1 (air = 1)	Adjudicated
Solubility (water)	Completely miscible with water	Adjudicated
Refractive Index (nD 20)	1.376 - 1.378	Interpreted
Viscosity	2.3–2.4 mPa·s at 20 °C	Adjudicated

Polar solvent — purity vs. intended end-use (electronics, pharma, general industrial) is the dominant grade consideration. See application guidance for grade selection.


PROPERTY CURVES

Density vs. Temperature (100%)



Source: CRC Handbook of Chemistry & Physics (neat IPA)

Vapor Pressure vs. Temperature (100%)



Source: CRC Handbook of Chemistry & Physics (neat IPA)

Reference curves drawn from public engineering data. For engineering use, consult the cited source for the underlying tabulated values.

MATERIALS OF CONSTRUCTION SERVICE ENVELOPE ≈ 99.9%

MATERIAL	RATING	MAX T (°C)	NOTES	SOURCE
Buna-N (NBR) Elastomer	Good	—	Minor to moderate effect.	CP Lab Safety Chemical Compatibility Chart
EPDM Elastomer	Excellent	—	Excellent compatibility.	CP Lab Safety Chemical Compatibility Chart
Viton (FKM) Elastomer	Excellent	—	Excellent.	CP Lab Safety Chemical Compatibility Chart
FFKM (Kalrez) Fluoropolymer	Excellent	200	Premium ester / ketone sealing	Cole-Parmer Chemical Compatibility
PTFE Fluoropolymer	Excellent	48	Excellent; satisfactory to 120 °F (48 °C).	CP Lab Safety Chemical Compatibility Chart
Borosilicate Glass Glass Ceramic	Excellent	100	Universally inert.	Cole-Parmer Chemical Compatibility
316L Stainless Steel Metal	Excellent	80	Inert; preferred for high-purity solvent service.	Cole-Parmer Chemical Compatibility

MATERIAL	RATING	MAX T (°C)	NOTES	SOURCE
Aluminium Metal	Good	—	Good: minor effect, slight corrosion or discoloration.	CP Lab Safety Chemical Compatibility Chart
Carbon Steel Metal	Excellent	—	Excellent.	CP Lab Safety Chemical Compatibility Chart
Stainless Steel Metal	Good	—	Good: minor effect, slight corrosion or discoloration.	CP Lab Safety Chemical Compatibility Chart
HDPE Thermoplastic	Fair	40	Swells with many polar solvents; verify per solvent.	Cole-Parmer Chemical Compatibility
LDPE Thermoplastic	Excellent	48	Excellent; satisfactory to 120 °F (48 °C).	CP Lab Safety Chemical Compatibility Chart
Polypropylene (PP) Thermoplastic	Excellent	48	Excellent; satisfactory to 120 °F (48 °C).	CP Lab Safety Chemical Compatibility Chart
PP Thermoplastic	Good	50	Acceptable but watch swelling with esters	Cole-Parmer Chemical Compatibility
PVC Thermoplastic	Excellent	22	Excellent; satisfactory to 72 °F (22 °C).	CP Lab Safety Chemical Compatibility Chart

Ratings reflect the service envelope (concentration × temperature) shown. Always confirm against your specific duty cycle and contact-time before equipment selection. The most cautious rating across overlapping references is shown.

REGULATORY & TRANSPORT

DOT / 49 CFR

UN NUMBER
UN1219 Adjudicated

HAZARD CLASS
3 Adjudicated

PACKING GROUP
II Adjudicated

PROPER SHIPPING NAME
Isopropanol or isopropyl alcohol Adjudicated

GHS / OSHA HCS 2024

SIGNAL WORD
Danger Adjudicated

H-CODES (HAZARD STATEMENTS)
H225, H319, H336 ECHA C&L Inventory

P-CODES (PRECAUTIONARY STATEMENTS)
P210, P233, P240, P241, P242, P243, P261, P264, P271, P280, P303+P361+P353, P304+P340, P305+P351+P338, P312, P337+P313, P370+P378, P403+P233, P403+P235, P405, P501

ECHA C&L Inventory

OCCUPATIONAL EXPOSURE LIMITS

OSHA PEL (29 CFR 1910.1000)
400 ppm TWA OSHA 29 CFR 1910.1000

ACGIH TLV
200 ppm TWA / 400 ppm STEL Adjudicated

NIOSH REL
400 ppm TWA / 500 ppm STEL NIOSH Pocket Guide

NIOSH IDLH
2000 ppm NIOSH Pocket Guide

REGIONAL CLASSIFICATIONS

EC NUMBER (EU EINECS)
200-661-7 Web SDS consensus

REACH SVHC
Not listed Web SDS consensus

CALIFORNIA PROP 65
Not listed Web SDS consensus

WGK WATER HAZARD (DE)
1 Web SDS consensus

TDG CLASSIFICATION (CANADA)
un1219, class 3, pg ii Web SDS consensus

Transport descriptions reflect 49 CFR 172.101 lookup at time of publication. Sourced data: NIOSH Pocket Guide for REL/IDLH, OSHA Z-Tables for PEL. Always verify against the latest regulatory text before shipment-critical decisions.

HEALTH & FIRE HAZARD

NFPA 704



- Health: 1 Web SDS consensus
- Fire: 3 Web SDS consensus
- Reactivity: 0 Web SDS consensus
- Specific: —

HMIS III

Health	1	Web SDS consensus
Flammability	3	Web SDS consensus
Physical Hazard	0	Web SDS consensus
PPE	B	Web SDS consensus

ACUTE TOXICOLOGY

LD_{50} ORAL (RAT)

5045 mg/kg

Web SDS consensus

LD_{50} DERMAL (RABBIT)

12800 mg/kg

Web SDS consensus

LC_{50} INHALATION (RAT, 4 H)

16000 ppm Web SDS consensus

NFPA 704 ratings 0 (no hazard) – 4 (severe hazard) per NFPA 704 standard. HMIS III ratings 0 – 4 per the American Coatings Association. Acute toxicology values from SDS Section 11 or NIOSH RTECS.

CATALOG EQUIVALENTS CROSS-REFERENCE VS MAJOR CHEMICAL SUPPLIERS

HONEYWELL

SKU	GRADE	CONC.	MATCH	NOTES
277-1	HPLC	≥99.9%	Unverified candidate	Honeywell HPLC grade; tighter residue spec than ACS.

SIGMA-ALDRICH

SKU	GRADE	CONC.	MATCH	NOTES
190764	ACS Reagent	99.5%	Unverified candidate	ACS Reagent ≥99.5%

THERMOFISHER

SKU	GRADE	CONC.	MATCH	NOTES
A416-4	ACS	99.5%	Unverified candidate	Optima LC/MS grade equivalent

Cross-references are informational. Confirm against the manufacturer's current specification before substitution. Competitor trademarks are property of their respective owners.

APPLICATIONS

Commercial manufacturing, laboratory or research use; may be used as an excipient or process solvent for pharmaceutical purposes (not as an active drug ingredient, medical device, or disinfectant)

chemsavers.com

Applications are drawn from published manufacturer and supplier documentation; each is sourced. Suitability for a specific use is the buyer's to confirm.

STORAGE & HANDLING

RECOMMENDED STORAGE

Store in tightly closed original containers in a cool, dry, well-ventilated flammable-liquids area that meets NFPA 30, away from heat, sparks and open flame. Ground and bond containers and equipment when transferring: vapor can be ignited by static discharge. Do not store with oxidizing agents, strong acids, peroxides, aldehydes, halogens, ammonia, acid anhydrides or alkali metals.

Adjudicated

HANDLING PRECAUTIONS

Use chemical-resistant gloves and splash goggles. Bond and ground during transfer to prevent static accumulation. Eliminate ignition sources within vapor envelope.

Class-level guidance — not product-specific; the SDS controls.

INCOMPATIBILITIES

Strong oxidizing agents; strong acids and acid anhydrides; peroxides; aldehydes; halogens; ammonia and amines; alkali metals, potassium and aluminum; iron salts. May attack some plastics and rubber.

Adjudicated

SHELF LIFE

Consult Technical Services for product-specific shelf life

For full hazard, PPE, and emergency response guidance, refer to the Safety Data Sheet (SDS) for this product. The SDS controls in all cases where guidance differs.

PACKAGING & LOGISTICS

SHIPPING DESCRIPTION (US DOT)

```
UN1219, Isopropanol or isopropyl alcohol, 3, PG II
```

Sourced from 49 CFR 172.101. Confirm against shipping documents and carrier requirements before tender.

NMFC CLASS	PLACARD	PACKING GROUP
70	Flammable Liquid	PG II

REVISION HISTORY

Last reviewed 2026-10-13 by Andre Taki, Chief Commercial Officer, DOT Hazmat–certified (49 CFR 172.704).

VERSION	DATE	CHANGE	TRIGGER
1.5	2026-10-13	Canonical data updated: 4 fields changed via the provenance/adjudication pipeline. • storage_precautions · canonical change (coa.data_provenance / adjudication) • incompatible_materials · canonical change (coa.data_provenance / adjudication) • conditions_to_avoid · canonical change (coa.data_provenance / adjudication) • hazardous_decomposition_products · canonical change (coa.data_provenance / adjudication)	canonical_change
1.4	2026-10-05	Canonical data updated: 20 fields changed via the provenance/adjudication pipeline. • oel_niosh_rel · canonical change (coa.data_provenance / adjudication) • oel_idlh · canonical change (coa.data_provenance / adjudication) • oel_osha_pel · canonical change (coa.data_provenance / adjudication) • recommended_use · canonical change (coa.data_provenance / adjudication) • synonyms · canonical change (coa.data_provenance / adjudication) • restrictions_on_use · canonical change (coa.data_provenance / adjudication) • odor · canonical change (coa.data_provenance / adjudication) • odorThreshold · canonical change (coa.data_provenance / adjudication) • meltingPoint · canonical change (coa.data_provenance / adjudication) • boilingPoint · canonical change (coa.data_provenance / adjudication) • flashPoint · canonical change (coa.data_provenance / adjudication) • vaporPressure · canonical change (coa.data_provenance / adjudication) • vaporDensity · canonical change (coa.data_provenance / adjudication) • specificGravity · canonical change (coa.data_provenance / adjudication) • solubility · canonical change (coa.data_provenance / adjudication) • explosiveLimits · canonical change (coa.data_provenance / adjudication) • autoIgnitionTemperature · canonical change (coa.data_provenance / adjudication) • partitionCoefficient · canonical change (coa.data_provenance / adjudication) • viscosity · canonical change (coa.data_provenance / adjudication) • oel_acgih_tlv · canonical change (coa.data_provenance / adjudication)	canonical_change
1.3	2026-09-30	Canonical data updated: 4 fields changed via the provenance/adjudication pipeline. • boilingPoint · canonical change (coa.data_provenance / adjudication) • meltingPoint · canonical change (coa.data_provenance / adjudication) • flashPoint · canonical change (coa.data_provenance / adjudication) • appearance · canonical change (coa.data_provenance / adjudication)	canonical_change

VERSION	DATE	CHANGE	TRIGGER
1.2	2026-07-22	Canonical data updated: 2 fields changed via the provenance/adjudication pipeline. • dotSubsidiaryHazardClass · canonical change (coa.data_provenance / adjudication) • dotProperShippingName · canonical change (coa.data_provenance / adjudication)	canonical_change
1.1	2026-06-18	Canonical data re-verified: 25 fields updated against independent vendor SDSs, CLP Annex VI, 49 CFR, and OSHA HazCom 2024 (GHS classification, hazard/precautionary codes, signal word, physical properties as applicable). • acs_compliance · canonical adjudication / reground (coa.data_provenance) • countryOfOrigin · canonical adjudication / reground (coa.data_provenance) • ec_number · canonical adjudication / reground (coa.data_provenance) • ghsClassification · canonical adjudication / reground (coa.data_provenance) • hmis_flammability · canonical adjudication / reground (coa.data_provenance) • hmis_health · canonical adjudication / reground (coa.data_provenance) • hmis_physical · canonical adjudication / reground (coa.data_provenance) • hmis_ppe · canonical adjudication / reground (coa.data_provenance) • hsCode · canonical adjudication / reground (coa.data_provenance) • inchi · canonical adjudication / reground (coa.data_provenance) • inchi_key · canonical adjudication / reground (coa.data_provenance) • iupac_name · canonical adjudication / reground (coa.data_provenance) • lc50_inhalation_rat_4h · canonical adjudication / reground (coa.data_provenance) • ld50_dermal_rabbit · canonical adjudication / reground (coa.data_provenance) • ld50_oral_rat · canonical adjudication / reground (coa.data_provenance) • nfpa_fire · canonical adjudication / reground (coa.data_provenance) • nfpa_health · canonical adjudication / reground (coa.data_provenance) • nfpa_reactivity · canonical adjudication / reground (coa.data_provenance) • prop_65_listed · canonical adjudication / reground (coa.data_provenance) • pubchem_cid · canonical adjudication / reground (coa.data_provenance) • reach_svhc_listed · canonical adjudication / reground (coa.data_provenance) • smiles · canonical adjudication / reground (coa.data_provenance) • tdg_classification · canonical adjudication / reground (coa.data_provenance) • usp_compliance · canonical adjudication / reground (coa.data_provenance) • wgk_water_hazard · canonical adjudication / reground (coa.data_provenance)	canonical_change

VERSION	DATE	CHANGE	TRIGGER
1.0	2026-05-20	Initial URL-first TDS published from canonical chemistry registry.	initial

This Technical Data Sheet is provided for technical reference. The Safety Data Sheet (SDS) controls in all cases where guidance differs. Values reflect Alliance Chemical canonical data at time of generation; subsequent revisions are recorded in the Revision History above.