

TECHNICAL DATA SHEET

Nitric Acid 65%ACS Grade

ACS Grade · 65%

CAS NUMBER

7697-37-2

ALLIANCE CODE

nitric-acid-65

GENERATED

2026-07-17

1. IDENTITY & COMPOSITION

PRODUCT NAME

Nitric Acid 65%ACS Grade

ALLIANCE CODE

nitric-acid-65

GRADE

ACS Grade

CONCENTRATION

65%

CAS NUMBER

7697-37-2 [PubChem](#)

FORMULA

HNO₃ [PubChem](#)

MOLECULAR WEIGHT

63.013 [PubChem](#)

PRODUCT TYPE

solution

PHYSICAL & CHEMICAL PROPERTIES

One or more physical-property values are temporarily suppressed pending verification against vendor COA data. For complete properties refer to the Safety Data Sheet (SDS) or contact sales@alliancechemical.com.

FORM

Liquid [Product record](#)

ODOR

Characteristic choking odor [Product record](#)

SPECIFIC GRAVITY (20 °C)

1.391 [Product record](#)

DENSITY

1.391 (65% w/w aqueous solution, 20 °C)

[Product record](#)

BOILING POINT

Not characterized for the 65% solution

[Product record](#)

MELTING POINT

Not characterized for the 65% solution

[Product record](#)

VAPOR PRESSURE

48 mmHg (NIOSH, 2024) [Product record](#)

SOLUBILITY (WATER)

Miscible (NIOSH, 2024) [Product record](#)

Strong acid — density and vapor-pressure values shown are at 20 °C; values shift markedly with concentration and temperature. Reference concentration-temperature curves before specifying equipment.

MATERIALS OF CONSTRUCTION SERVICE ENVELOPE ≈ 65%

MATERIAL	RATING	MAX T (°C)	NOTES	SOURCE
Buna-N (NBR) Elastomer	Poor	—	Swells and degrades	Cole-Parmer Chemical Compatibility
EPDM Elastomer	Good	40	Acceptable but FKM preferred	Cole-Parmer Chemical Compatibility
Viton (FKM) Elastomer	Excellent	80	Preferred elastomer	Cole-Parmer Chemical Compatibility
PTFE Fluoropolymer	Excellent	200	Lining and gaskets	Cole-Parmer Chemical Compatibility
Borosilicate Glass Glass Ceramic	Excellent	100	Inert to most strong acids (avoid HF).	Cole-Parmer Chemical Compatibility
Glass (borosilicate) Glass Ceramic	Excellent	100	Inert under all conditions	Cole-Parmer Chemical Compatibility
316 stainless steel Metal	Poor	25	Severe pitting; use only for vapors	Cole-Parmer Chemical Compatibility
Aluminium Metal	Not recommended	—	Reacts to form H ₂ gas	Cole-Parmer Chemical Compatibility
Carbon steel Metal	Not recommended	—	Aggressive corrosion	Cole-Parmer Chemical Compatibility
Carbon Steel Metal	Not recommended	—	Catastrophic corrosion; never use.	Cole-Parmer Chemical Compatibility
Hastelloy C-276 Metal	Excellent	90	Premium HCl alloy	Cole-Parmer Chemical Compatibility

MATERIAL	RATING	MAX T (°C)	NOTES	SOURCE
Inconel 625 Metal	Good	60	Acceptable for dilute service	Cole-Parmer Chemical Compatibility
Tantalum Metal	Excellent	100	Best-in-class but expensive	Cole-Parmer Chemical Compatibility
CPVC Thermoplastic	Excellent	90	Preferred for elevated temperature	Cole-Parmer Chemical Compatibility
FRP (vinyl ester) Thermoplastic	Good	60	Common bulk-storage tank material	Cole-Parmer Chemical Compatibility
HDPE Thermoplastic	Excellent	60	Standard drum / IBC material	Cole-Parmer Chemical Compatibility
PVC Thermoplastic	Excellent	60	Standard piping for ambient service	Cole-Parmer Chemical Compatibility

Ratings reflect the service envelope (concentration × temperature) shown. Always confirm against your specific duty cycle and contact-time before equipment selection. The most cautious rating across overlapping references is shown.

REGULATORY & TRANSPORT

DOT / 49 CFR

UN NUMBER

UN2031 [Vendor Label](#)

PACKING GROUP

II [Adjudicated](#)

HAZARD CLASS

8 [Adjudicated](#)

PROPER SHIPPING NAME

Nitric acid, other than red fuming, with at least 65 percent, but not more than 70 percent nitric acid [Adjudicated](#)

GHS / OSHA HAZCOM 2012

SIGNAL WORD

Danger [Adjudicated](#)

H-CODES (HAZARD STATEMENTS)

H272, H290, H314, EUH071 [ECHA CLP Annex VI](#)

P-CODES (PRECAUTIONARY STATEMENTS)

P210, P220, P234, P260, P264, P271, P280, P284,
P301+P330+P331, P303+P361+P353, P304+P340,
P305+P351+P338, P310, P320, P321, P363,...

OCCUPATIONAL EXPOSURE LIMITS

OSHA PEL (29 CFR 1910.1000)

2 ppm TWA [OSHA 29 CFR 1910.1000](#)

ACGIH TLV

— [unknown](#)

NIOSH REL

2 ppm TWA / 4 ppm STEL [NIOSH Pocket Guide](#)

NIOSH IDLH

25 ppm [NIOSH Pocket Guide](#)

Transport descriptions reflect 49 CFR 172.101 lookup at time of publication. Sourced data: ECHA CLP Annex VI for harmonised classifications, NIOSH Pocket Guide for REL/IDLH, OSHA Z-Tables for PEL. Always verify against the latest regulatory text before shipment-critical decisions.

Supplier Qualification Packet

One zipped download containing the TDS, SDS, latest lot COA (when available), and a fresh Letter of Continuing Guaranty for Nitric Acid 65%ACS Grade. Every file included is SHA-256 hashed and listed in a manifest your QA team can audit.

CATALOG EQUIVALENTS CROSS-REFERENCE VS MAJOR CHEMICAL SUPPLIERS

SIGMA-ALDRICH

SKU	GRADE	CONC.	MATCH	NOTES
438073	ACS Reagent	70%	Exact	ACS Reagent fuming-free 70%

Cross-references are informational. Confirm against the manufacturer's current specification before substitution. Competitor trademarks are property of their respective owners.

APPLICATION GUIDANCE

Nitric Acid 65%ACS Grade (ACS Grade) is a strong mineral acid used across pH control, metal pickling, food and beverage processing, and chemical synthesis. Grade and concentration determine the appropriate end-use and materials.

- Metal pickling, etching, and surface preparation
- pH adjustment in water and wastewater treatment
- Regeneration of ion-exchange resins
- Chemical manufacturing and synthesis
- Food and beverage processing (food-grade only)

Always add acid to water, never water to acid. Use lined or fluoropolymer piping rated for the concentration; carbon steel is not suitable for dilute acid service.

STORAGE & HANDLING

RECOMMENDED STORAGE

Cool, dry, well-ventilated area in compatible containers (lined steel, HDPE, FRP — verify per concentration). Segregate from bases, oxidizers,...

INCOMPATIBILITIES

Bases, active metals (aluminium, zinc), cyanides, sulfides, oxidizing agents. Reacts violently with organic anhydrides.

HANDLING PRECAUTIONS

Use full PPE including face shield, acid-resistant gloves and apron. Add acid to water slowly with stirring; never reverse. Ventilation required.

SHELF LIFE

24 months from date of manufacture in sealed, original packaging

For full hazard, PPE, and emergency response guidance, refer to the Safety Data Sheet (SDS) for this product. The SDS controls in all cases where guidance differs.

PACKAGING & LOGISTICS

SHIPPING DESCRIPTION (US DOT)

UN2031, Nitric acid, other than red fuming, with at least 65 percent, but not more than 70 percent nitric acid, 8, PG II

Sourced from 49 CFR 172.101. Confirm against shipping documents and carrier requirements before tender.

NMFC CLASS 60	PLACARD Corrosive	PACKING GROUP PG II
------------------	----------------------	------------------------

REVISION HISTORY

Last reviewed 2026-05-20 by Hossein Taki, Vice President (Vice President, Alliance Chemical · CAGE Code 1LT50 · DOT Hazmat Registrant #2188383).

VERSION	DATE	CHANGE	TRIGGER
1.0	2026-05-20	Initial URL-first TDS published from canonical chemistry registry.	initial

This Technical Data Sheet is provided for technical reference. The Safety Data Sheet (SDS) controls in all cases where guidance differs. Values reflect Alliance Chemical canonical data at time of generation; subsequent revisions are recorded in the Revision History above.

ALLIANCE CHEMICAL

Order Nitric Acid 65%ACS Grade

Bulk & packaged sizes · COA/SDS ships with every order