

TECHNICAL DATA SHEET

Phosphoric Acid 75% USP Food Grade

USP Food Grade · 75%

CAS NUMBER	ALLIANCE CODE	GENERATED
7664-38-2	phosphoric-acid-75-usp-food-grade	2026-08-31
REVISION	REVIEWED	
1.2	2026-07-17 · Andre Taki	

IDENTITY & COMPOSITION

PRODUCT NAME	ALLIANCE CODE
Phosphoric Acid 75% USP Food Grade	phosphoric-acid-75-usp-food-grade
GRADE	CONCENTRATION
USP Food Grade	75%
CAS NUMBER	FORMULA
7664-38-2 PubChem	H3O4P PubChem
MOLECULAR WEIGHT	PRODUCT TYPE
97.995 PubChem	solution

SPECIFICATIONS

TEST	SPECIFICATION	TYPICAL	METHOD	SOURCE
Assay (H3PO4)	74.5 – 75.5 %	75.0 %	acidimetry	Commercial practice
Arsenic (As)	Not more than 3 mg/kg	0.088 mg/kg	—	FCC
Cadmium (Cd)	Not more than 3 mg/kg	0.044 mg/kg	—	FCC

TEST	SPECIFICATION	TYPICAL	METHOD	SOURCE
Chlorides (Cl)	10 ppm Cl maximum	1.3 ppm	—	Supplier specification
Fluoride (F)	Not more than 10 mg/kg	1.8 mg/kg	—	FCC
Iron (Fe)	10 ppm Fe maximum	1.8 ppm	—	Supplier specification
Lead (Pb)	Not more than 3 mg/kg	0.044 mg/kg	—	FCC
Identification (phosphate)	A 1:10 aqueous solution gives positive tests for Phosphate	Passes test	—	FCC
Sulfate (SO ₄)	100 ppm SO ₄ maximum	18 ppm	—	Supplier specification
Mercury (Hg)	Not more than 1 mg/kg	0.018 mg/kg	Cold-vapour AAS (EPA 245.1)	Interpreted

Specification values are guaranteed limits. Typical values are representative of production lots and are not guaranteed. Lot-specific certificates of analysis ship with every order.

AVAILABLE GRADES SAME CAS, ALTERNATE GRADES AND CONCENTRATIONS

GRADE	CONCENTRATION	TYPICAL ASSAY	SKU
THIS GRADE USP Food Grade	75%	—	current
—	75%	—	phosphoric-acid-75
ACS	50%	—	phosphoric-acid-50-acs-grade
Technical	50%	—	phosphoric-acid-50-technical-grade

GRADE	CONCENTRATION	TYPICAL ASSAY	SKU
ACS	30%	—	phosphoric-acid-30-acs-grade
Reagent	30%	—	phosphoric-acid-30-the-ultimate-rust-remover-solution
Food	20%	—	phosphoric-acid-20-food-grade
Technical	20%	—	phosphoric-acid-20-technical-grade
Technical	10%	—	phosphoric-acid-10-technical-grade
Food	5%	—	phosphoric-acid-5-food-grade
Technical	5%	—	phosphoric-acid-5-technical-grade
Food	—	—	phosphoric-acid-45-food-grade
Technical	—	—	phosphoric-acid-45-technical-grade

Typical assay shown is the rolling-window mean from the sibling product's most recent lots. Grade selection drives downstream end-use — verify the sibling grade matches your specification before substitution.

PHYSICAL & CHEMICAL PROPERTIES

PROPERTY	VALUE	SOURCE
Appearance	Clear, colorless viscous liquid	Published reference
Form	Liquid	Published reference
Color	10 APHA Units	Supplier specification
Odor	Odorless	Published reference
pH	pH = 1.5 (0.1 N aqueous solution)	Published reference
Specific Gravity (20 °C)	1.574 – 1.580	Supplier specification
Density	≈1.575 (75% solution, 25 °C)	Published reference
Boiling Point	~135–158 °C	Published reference
Melting Point	~ -17 to 21 °C (freezing point)	Published reference
Flash Point	Non-flammable	Published reference
Vapor Pressure	Low	Published reference
Solubility (water)	Miscible (NIOSH, 2024)	Published reference

Strong acid — density and vapor-pressure values shown are at 20 °C; values shift markedly with concentration and temperature. Reference concentration-temperature curves before specifying equipment.

MATERIALS OF CONSTRUCTION SERVICE ENVELOPE ≈ 75%

MATERIAL	RATING	MAX T (°C)	NOTES	SOURCE
Buna-N (NBR) Elastomer	Poor	—	Swells and degrades	Cole-Parmer Chemical Compatibility
EPDM Elastomer	Good	40	Acceptable but FKM preferred	Cole-Parmer Chemical Compatibility

MATERIAL	RATING	MAX T (°C)	NOTES	SOURCE
Viton (FKM) Elastomer	Excellent	80	Preferred elastomer	Cole-Parmer Chemical Compatibility
PTFE Fluoropolymer	Excellent	200	Universal acid compatibility.	Cole-Parmer Chemical Compatibility
Borosilicate Glass Glass Ceramic	Excellent	100	Inert to most strong acids (avoid HF).	Cole-Parmer Chemical Compatibility
Glass (borosilicate) Glass Ceramic	Excellent	100	Inert under all conditions	Cole-Parmer Chemical Compatibility
316 stainless steel Metal	Poor	25	Severe pitting; use only for vapors	Cole-Parmer Chemical Compatibility
Aluminium Metal	Not recommended	—	Reacts to form H ₂ gas	Cole-Parmer Chemical Compatibility
Carbon Steel Metal	Not recommended	—	Catastrophic corrosion; never use.	Cole-Parmer Chemical Compatibility
Hastelloy C-276 Metal	Excellent	90	Premium HCl alloy	Cole-Parmer Chemical Compatibility
Inconel 625 Metal	Good	60	Acceptable for dilute service	Cole-Parmer Chemical Compatibility
Tantalum Metal	Excellent	100	Best-in-class but expensive	Cole-Parmer Chemical Compatibility
CPVC Thermoplastic	Excellent	90	Preferred for elevated temperature	Cole-Parmer Chemical Compatibility

MATERIAL	RATING	MAX T (°C)	NOTES	SOURCE
FRP (vinyl ester) Thermoplastic	Good	60	Common bulk-storage tank material	Cole-Parmer Chemical Compatibility
HDPE Thermoplastic	Excellent	60	Standard drum / IBC material	Cole-Parmer Chemical Compatibility
PVC Thermoplastic	Excellent	60	Standard piping for ambient service	Cole-Parmer Chemical Compatibility

Ratings reflect the service envelope (concentration × temperature) shown. Always confirm against your specific duty cycle and contact-time before equipment selection. The most cautious rating across overlapping references is shown.

REGULATORY & TRANSPORT

DOT / 49 CFR

UN NUMBER	HAZARD CLASS
UN1805 Adjudicated	8 Adjudicated
PACKING GROUP	PROPER SHIPPING NAME
III Adjudicated	Phosphoric acid solution Adjudicated

GHS / OSHA HAZCOM 2012

SIGNAL WORD	H-CODES (HAZARD STATEMENTS)
Danger Adjudicated	H290, H314 ECHA CLP Annex VI
P-CODES (PRECAUTIONARY STATEMENTS)	
P234, P260, P264, P280, P301+P330+P331, P303+P361+P353, P304+P340, P305+P351+P338, P310, P321, P363, P405, P501	
Adjudicated	

OCCUPATIONAL EXPOSURE LIMITS

OSHA PEL (29 CFR 1910.1000)	ACGIH TLV
1 mg/m³ TWA OSHA 29 CFR 1910.1000	— no canonical
NIOSH REL	NIOSH IDLH
1 mg/m³ TWA / 3 mg/m³ STEL	1000 mg/m³ NIOSH Pocket Guide
NIOSH Pocket Guide	

Transport descriptions reflect 49 CFR 172.101 lookup at time of publication. Sourced data: ECHA CLP Annex VI for harmonised classifications, NIOSH Pocket Guide for REL/IDLH, OSHA Z-Tables for PEL. Always verify against the latest regulatory text before shipment-critical decisions.

CATALOG EQUIVALENTS CROSS-REFERENCE VS MAJOR CHEMICAL SUPPLIERS

SIGMA-ALDRICH

SKU	GRADE	CONC.	MATCH	NOTES
345245	ACS Reagent	85%	Exact	ACS Reagent ≥85%

Cross-references are informational. Confirm against the manufacturer's current specification before substitution. Competitor trademarks are property of their respective owners.

APPLICATIONS

Fertilizer manufacture, and use as a pH modifier, sanitizing agent and rust converter labelley.com

Bulk food chemical and bulk pharmaceutical chemical for manufacturing, processing or repackaging

digitalassets.avantorsciences.com

Miscellaneous or general purpose food additive, GRAS under 21 CFR 182.1073 static1.squarespace.com

Miscellaneous or general purpose feed additive, GRAS under 21 CFR 582.1073

static1.squarespace.com

Acidifying agent in meat and poultry products and margarine; antioxidant synergist in lard, shortening and poultry fats

static1.squarespace.com

Applications are drawn from published manufacturer and supplier documentation; each is sourced. Suitability for a specific use is the buyer's to confirm.

STORAGE & HANDLING

RECOMMENDED STORAGE

Cool, dry, well-ventilated area in compatible containers (lined steel, HDPE, FRP — verify per concentration). Segregate from bases, oxidizers, metals, and cyanides.

Class-level guidance — not product-specific; the SDS controls.

INCOMPATIBILITIES

Bases, active metals (aluminium, zinc), cyanides, sulfides, oxidizing agents. Reacts violently with organic anhydrides.

Class-level guidance — not product-specific; the SDS controls.

HANDLING PRECAUTIONS

Use full PPE including face shield, acid-resistant gloves and apron. Add acid to water slowly with stirring; never reverse. Ventilation required.

Class-level guidance — not product-specific; the SDS controls.

SHELF LIFE

Consult Technical Services for product-specific shelf life

For full hazard, PPE, and emergency response guidance, refer to the Safety Data Sheet (SDS) for this product. The SDS controls in all cases where guidance differs.

PACKAGING & LOGISTICS

SHIPPING DESCRIPTION (US DOT)

UN1805, Phosphoric acid solution, 8, PG III

Sourced from 49 CFR 172.101. Confirm against shipping documents and carrier requirements before tender.

NMFC CLASS 65	PLACARD Corrosive	PACKING GROUP PG III
------------------	----------------------	-------------------------

REVISION HISTORY

Last reviewed 2026-07-17 by Andre Taki, DOT Hazmat Specialist.

VERSION	DATE	CHANGE	TRIGGER
1.2	2026-07-22	Canonical data updated: 2 fields changed via the provenance/adjudication pipeline. - dotSubsidiaryHazardClass · canonical change (coa.data_provenance / adjudication) - dotProperShippingName · canonical change (coa.data_provenance / adjudication)	canonical_change
1.1	2026-07-17	Canonical data re-verified: 5 fields updated against independent vendor SDSs, CLP Annex VI, 49 CFR, and OSHA HazCom 2024 (GHS classification, hazard/precautionary codes, signal word, physical properties as applicable). - countryOfOrigin · canonical adjudication / reground (coa.data_provenance) - ghsClassification · canonical adjudication / reground (coa.data_provenance) - hazard_p_codes · canonical adjudication / reground (coa.data_provenance) - hsCode · canonical adjudication / reground (coa.data_provenance) - physicalProperties · canonical adjudication / reground (coa.data_provenance)	canonical_change
1.0	2026-05-20	Initial URL-first TDS published from canonical chemistry registry.	initial

This Technical Data Sheet is provided for technical reference. The Safety Data Sheet (SDS) controls in all cases where guidance differs. Values reflect Alliance Chemical canonical data at time of generation; subsequent revisions are recorded in the Revision History above.