

TECHNICAL DATA SHEET

Propylene Glycol 60% Inhibited

60%

CAS NUMBER	ALLIANCE CODE	GENERATED
57-55-6	propylene-glycol-60-inhibited	2026-09-01
REVISION	REVIEWED	
1.2	2026-06-17 · Andre Taki	

IDENTITY & COMPOSITION

PRODUCT NAME	ALLIANCE CODE
Propylene Glycol 60% Inhibited	propylene-glycol-60-inhibited
GRADE	CONCENTRATION
—	60%
CAS NUMBER	FORMULA
57-55-6 PubChem	C3H8O2 PubChem
MOLECULAR WEIGHT	PRODUCT TYPE
76.09 PubChem	mixture

SPECIFICATIONS

TEST	SPECIFICATION	TYPICAL	METHOD	SOURCE
Propylene glycol concentration	59.0 – 61.0 % v/v	60.0 %	—	Commercial practice
Burst protection	< -60 °F (< -51.1 °C) at 60 vol % propylene glycol	-75 °F (-59 °C)	ASTM D1177 / formulation table	Interpreted
Corrosion performance	Weight loss within ASTM D3306 limits on all six metals	Passes test	ASTM D1384	Interpreted

TEST	SPECIFICATION	TYPICAL	METHOD	SOURCE
Chloride in dilution water	< 25 ppm	0.5 ppm	ASTM D512	Interpreted
Acidity as Acetic Acid	0.003 % max	0.0009 wt%	—	Derived by dilution
Chlorides as Cl	0.76 ppm max	0.34 ppm	—	Derived by dilution
Heavy Metals as Pb	3 ppm max	0.15 ppm	—	Derived by dilution
Iron	0.6 ppm max	0.08 ppm	—	Derived by dilution
Dipropylene glycol (DPG)	0.3 wt% max	0.150 wt%	GC area % (ASTM E202)	Derived by dilution
ash	0.003% max	0.0005 wt%	—	Derived by dilution
Assay	59.0 – 61.0 %	60.0 %	—	Commercial practice
Reserve alkalinity	≥ 6.0 mL at 60 vol % propylene glycol	6.9	ASTM D1121	Commercial practice

Specification values are guaranteed limits. Typical values are representative of production lots and are not guaranteed. Lot-specific certificates of analysis ship with every order.

AVAILABLE GRADES SAME CAS, ALTERNATE GRADES AND CONCENTRATIONS

GRADE	CONCENTRATION	TYPICAL ASSAY	SKU
THIS GRADE —	60%	—	current
Technical	60%	—	propylene-glycol-60-technical-grade

GRADE	CONCENTRATION	TYPICAL ASSAY	SKU
USP	60%	—	propylene-glycol-60-usp-grade
USP Grade	50%	—	50-propylene-glycol-usp-grade
Technical Grade	40%	—	40-propylene-glycol-technical- grade
USP Grade	40%	—	40-propylene-glycol-usp-grade
—	20%	—	propylene-glycol-20-inhibited
Technical	20%	—	propylene-glycol-20-technical- grade
USP	20%	—	propylene-glycol-20-usp-grade
Technical Grade	—	—	propylene-glycol-technical-grade
USP Grade	—	—	propylene-glycol-usp-grade

Typical assay shown is the rolling-window mean from the sibling product's most recent lots. Grade selection drives downstream end-use — verify the sibling grade matches your specification before substitution.

PHYSICAL & CHEMICAL PROPERTIES

PROPERTY	VALUE	SOURCE
Appearance	Clear, colorless to pale liquid	Published reference
Odor	Mild, characteristic	Published reference
pH	9–10.5	Published reference
Specific Gravity (20 °C)	1.041 – 1.051	Published reference
Density	1.046 g/mL at 20 °C	Published reference
Boiling Point	225 °F at 60 vol % propylene glycol	Commercial practice
Melting Point	< –60 °F (–51.1 °C) at 60 vol % propylene glycol	Commercial practice
Flash Point	Not flammable (aqueous solution)	Published reference
Solubility (water)	Miscible with water	Published reference

REGULATORY & TRANSPORT

DOT / 49 CFR

UN NUMBER

Not regulated **Adjudicated**

PACKING GROUP

Not regulated **Adjudicated**

HAZARD CLASS

Not regulated **Adjudicated**

PROPER SHIPPING NAME

Not regulated **Adjudicated**

GHS / OSHA HAZCOM 2012

SIGNAL WORD

Not regulated **Adjudicated**

H-CODES (HAZARD STATEMENTS)

Not applicable **ECHA CLP Annex VI**

P-CODES (PRECAUTIONARY STATEMENTS)

Not applicable **ECHA CLP Annex VI**

OCCUPATIONAL EXPOSURE LIMITS

OSHA PEL (29 CFR 1910.1000)

— **no canonical**

ACGIH TLV

— **no canonical**

NIOSH REL

— **no canonical**

NIOSH IDLH

— **no canonical**

Transport descriptions reflect 49 CFR 172.101 lookup at time of publication. Sourced data: ECHA CLP Annex VI for harmonised classifications, NIOSH Pocket Guide for REL/IDLH, OSHA Z-Tables for PEL. Always verify against the latest regulatory text before shipment-critical decisions.

APPLICATION GUIDANCE

Propylene Glycol 60% Inhibited is a glycol-based heat-transfer and freeze-protection fluid. Concentration sets the freeze and burst protection; the inhibitor package sets how long the system stays protected from corrosion.

- Closed-loop heat transfer and process cooling
- Data-centre and chilled-water freeze protection
- HVAC hydronic loops and glycol makeup
- Freeze and burst protection for idle or seasonal systems
- Humectant and carrier applications (USP/food-grade propylene glycol only)

Verify concentration against the required freeze and burst protection, and confirm elastomer and metallurgy compatibility for the service temperature. Ethylene glycol is toxic by ingestion and must not be used where incidental food or potable contact is possible — specify a propylene glycol grade for those services.

STORAGE & HANDLING

RECOMMENDED STORAGE

Cool, dry, well-ventilated area in tightly sealed original containers. Neat glycols are combustible liquids with high flash points (roughly 99–111 °C) and do not require a solvent store; aqueous blends will not sustain combustion. Protect inhibited coolants from contamination and from freezing below their stated protection point.

Class-level guidance — not product-specific; the SDS controls.

INCOMPATIBILITIES

Strong oxidizers, strong acids and strong bases. Galvanized (zinc) surfaces are attacked by many inhibited coolant packages. Verify elastomer and gasket compatibility for the service temperature; EPDM is standard for glycol/water service.

Class-level guidance — not product-specific; the SDS controls.

For full hazard, PPE, and emergency response guidance, refer to the Safety Data Sheet (SDS) for this product. The SDS controls in all cases where guidance differs.

HANDLING PRECAUTIONS

Chemical-resistant gloves and splash goggles. Ethylene glycol grades are toxic by ingestion and must be kept away from food, drink and animals; propylene glycol grades are not. Avoid contact with hot surfaces and hot process equipment. Inhibitor packages deplete in service — monitor rather than top up blindly.

Class-level guidance — not product-specific; the SDS controls.

SHELF LIFE

Consult Technical Services for product-specific shelf life

PACKAGING & LOGISTICS

SHIPPING DESCRIPTION (US DOT)

Not regulated for transport.

Confirm against shipping documents and carrier requirements before tender.

NMFC CLASS
55

REVISION HISTORY

Last reviewed 2026-06-17 by Andre Taki, DOT Hazmat Specialist.

VERSION	DATE	CHANGE	TRIGGER
1.2	2026-07-24	Canonical data updated: 1 field changed via the provenance/adjudication pipeline. physicalProperties · canonical change (coa.data_provenance / adjudication)	canonical_change
1.1	2026-06-17	Canonical data re-verified: 3 fields updated against independent vendor SDSs, CLP Annex VI, 49 CFR, and OSHA HazCom 2024 (GHS classification, hazard/precautionary codes, signal word, physical properties as applicable). - countryOfOrigin · canonical adjudication / reground (coa.data_provenance) - dotSubsidiaryHazardClass · canonical adjudication / reground (coa.data_provenance) - hsCode · canonical adjudication / reground (coa.data_provenance)	canonical_change
1.0	2026-05-20	Initial URL-first TDS published from canonical chemistry registry.	initial

This Technical Data Sheet is provided for technical reference. The Safety Data Sheet (SDS) controls in all cases where guidance differs. Values reflect Alliance Chemical canonical data at time of generation; subsequent revisions are recorded in the Revision History above.