

TECHNICAL DATA SHEET

Sodium Chloride Technical Grade

ALLIANCE CODE	GENERATED	REVISION
SHOPIFY-7992479711274	2026-09-11	1.1
REVIEWED		
2026-08-25		

IDENTITY & COMPOSITION

PRODUCT NAME	ALLIANCE CODE
Sodium Chloride Technical Grade	SHOPIFY-7992479711274
GRADE	CONCENTRATION
—	—
CAS NUMBER	FORMULA
— no canonical	— no canonical
MOLECULAR WEIGHT	PRODUCT TYPE
— no canonical	—

SPECIFICATIONS

TEST	SPECIFICATION	TYPICAL	METHOD	SOURCE
Assay (NaCl, dry basis)	99.5% Min	99.9 %	—	Interpreted
Anti-Caking Agent	No	Passes test	—	Interpreted
Insolubles	Max 0.03 %	0.004 %	—	Interpreted
Yellow prussiate of soda (sodium ferrocyanide anticaking agent)	13PPM Max	4 PPM	—	Interpreted

TEST	SPECIFICATION	TYPICAL	METHOD	SOURCE
Sulfate (as SO ₄)	0.08% Max	0.035%	—	Interpreted
Calcium (Ca)	0.15% Max	0.012 %	—	Interpreted
Magnesium (Mg)	0.15% Max	0.003 %	—	Interpreted
Surface moisture	0.2% Max	0.03 %	—	Interpreted
Iron (Fe)	Max 10 ppm	0.6 ppm	ICP-OES / AAS after aqueous dissolution	Interpreted
Granulation – through USS No. 20 sieve (850 um)	Min 95 %	99.2 %	Dry sieve, ASTM E11 screens (ASTM D632 procedure)	Interpreted
loss on ignition	40 – 52 %	46 %	—	Interpreted
sieve – retained on pan	0 – 5 %	2.5 %	—	Interpreted
sieve – uss 4mesh retained	95 – 100 %	97.5 %	—	Interpreted

Specification values are guaranteed limits. Typical values are representative of production lots and are not guaranteed. Lot-specific certificates of analysis ship with every order.

PHYSICAL & CHEMICAL PROPERTIES

PROPERTY	VALUE	SOURCE
pH	6.0 – 9.0	Interpreted
Density	70 – 80 lb/ft ³	Interpreted

MATERIALS OF CONSTRUCTION

MATERIAL	RATING	MAX T (°C)	NOTES	SOURCE
Buna-N (NBR) Elastomer	Good	60	Acceptable	Cole-Parmer Chemical Compatibility
EPDM Elastomer	Excellent	100	Standard for brine gaskets.	Parker O-ring Chemical Compatibility
Viton (FKM) Elastomer	Excellent	100	Preferred elastomer	Cole-Parmer Chemical Compatibility
Borosilicate Glass Glass Ceramic	Excellent	100	Universally inert to salt solutions.	Cole-Parmer Chemical Compatibility
Concrete (sealed) Glass Ceramic	Good	—	Acceptable with epoxy coating	Cole-Parmer Chemical Compatibility
304 stainless steel Metal	Fair	25	Pitting in chloride-rich service	Cole-Parmer Chemical Compatibility
316L Stainless Steel Metal	Good	60	Watch for chloride pitting above 60 °C in chloride salts.	NACE Chloride Pitting Guidelines
Aluminium Metal	Poor	—	Pitting; not recommended for brine	Cole-Parmer Chemical Compatibility
Carbon steel Metal	Poor	—	Rapid rust in brine	Cole-Parmer Chemical Compatibility
FRP Thermoplastic	Excellent	60	Common bulk-storage	Cole-Parmer Chemical Compatibility
HDPE Thermoplastic	Excellent	60	Universal salt brine compatibility.	Cole-Parmer Chemical Compatibility
PP Thermoplastic	Excellent	80	Acceptable for hot brine	Cole-Parmer Chemical Compatibility

MATERIAL	RATING	MAX T (°C)	NOTES	SOURCE
PVC Thermoplastic	Excellent	60	Standard for brine piping.	Cole-Parmer Chemical Compatibility

Ratings reflect the service envelope (concentration × temperature) shown. Always confirm against your specific duty cycle and contact-time before equipment selection. The most cautious rating across overlapping references is shown.

REGULATORY & TRANSPORT

DOT / 49 CFR

UN NUMBER

Not regulated **Adjudicated**

HAZARD CLASS

Not regulated **Adjudicated**

PACKING GROUP

Not regulated **Adjudicated**

PROPER SHIPPING NAME

Not regulated **Adjudicated**

GHS / OSHA HAZCOM 2012

SIGNAL WORD

Not regulated **Adjudicated**

H-CODES (HAZARD STATEMENTS)

— **no canonical**

P-CODES (PRECAUTIONARY STATEMENTS)

— **no canonical**

OCCUPATIONAL EXPOSURE LIMITS

OSHA PEL (29 CFR 1910.1000)

— **no canonical**

ACGIH TLV

— **no canonical**

NIOSH REL

— **no canonical**

NIOSH IDLH

— **no canonical**

Transport descriptions reflect 49 CFR 172.101 lookup at time of publication. Sourced data: ECHA CLP Annex VI for harmonised classifications, NIOSH Pocket Guide for REL/IDLH, OSHA Z-Tables for PEL. Always verify against the latest regulatory text before shipment-critical decisions.

APPLICATIONS

Industrial-grade sodium chloride used for water softening **icl-industrialproducts.com**

Used in swimming pools **icl-industrialproducts.com**

Used in dishwashers **icl-industrialproducts.com**

Applications are drawn from published manufacturer and supplier documentation; each is sourced. Suitability for a specific use is the buyer's to confirm.

STORAGE & HANDLING

RECOMMENDED STORAGE

Cool, dry area in sealed containers. Many salts are hygroscopic — protect from atmospheric moisture, which can cause caking, hydrate formation, or reduced flow.

Class-level guidance — not product-specific; the SDS controls.

INCOMPATIBILITIES

Specific incompatibilities depend on the salt — consult the SDS. Many salts react with strong acids to release gases.

Class-level guidance — not product-specific; the SDS controls.

For full hazard, PPE, and emergency response guidance, refer to the Safety Data Sheet (SDS) for this product. The SDS controls in all cases where guidance differs.

HANDLING PRECAUTIONS

Standard chemical PPE — dust mask and goggles for handling of fine grades. Avoid generating airborne dust.

Class-level guidance — not product-specific; the SDS controls.

SHELF LIFE

Consult Technical Services for product-specific shelf life

PACKAGING & LOGISTICS

SHIPPING DESCRIPTION (US DOT)

Not regulated for transport.

Confirm against shipping documents and carrier requirements before tender.

NMFC CLASS

55

Freight classification is a fallback estimate. Verify with carrier before tender.

REVISION HISTORY

VERSION	DATE	CHANGE	TRIGGER
1.1	2026-08-25	Canonical data updated: 5 fields changed via the provenance/adjudication pipeline. • <code>unNumber</code> · canonical change (coa.data_provenance / adjudication) • <code>hazardClass</code> · canonical change (coa.data_provenance / adjudication) • <code>packingGroup</code> · canonical change (coa.data_provenance / adjudication) • <code>dotProperShippingName</code> · canonical change (coa.data_provenance / adjudication) • <code>signalWord</code> · canonical change (coa.data_provenance / adjudication)	canonical_change

This Technical Data Sheet is provided for technical reference. The Safety Data Sheet (SDS) controls in all cases where guidance differs. Values reflect Alliance Chemical canonical data at time of generation; subsequent revisions are recorded in the Revision History above.