

TECHNICAL DATA SHEET

Trisodium Phosphate Dodecahydrate - ACS Reagent Grade

ACS Reagent

CAS NUMBER	ALLIANCE CODE	GENERATED
10101-89-0	trisodium-phosphate-dodecahydrate-ac-s-reagent-grade	2026-08-31
REVISION	REVIEWED	
1.2	2026-07-17 · Andre Taki	

IDENTITY & COMPOSITION

PRODUCT NAME	ALLIANCE CODE
Trisodium Phosphate Dodecahydrate - ACS Reagent Grade	trisodium-phosphate-dodecahydrate-ac-s-reagent-grade
GRADE	CONCENTRATION
ACS Reagent	—
CAS NUMBER	FORMULA
10101-89-0 PubChem	H24Na3O16P PubChem
MOLECULAR WEIGHT	PRODUCT TYPE
380.12 PubChem	pure_substance

SPECIFICATIONS

TEST	SPECIFICATION	TYPICAL	METHOD	SOURCE
Assay (Na3PO4·12H2O)	98.0 – 102.0 %	100.0 %	—	ACS Reagent Chemicals
Chloride (Cl)	≤0.001%	0.0002 %	—	Supplier specification

TEST	SPECIFICATION	TYPICAL	METHOD	SOURCE
Excess alkali (as NaOH)	≤2.5%	1.5 %	—	Supplier specification
Heavy metals (as Pb)	≤0.001%	0.0001 %	—	Supplier specification
Insoluble matter	0.01 % maximum	0.002 %	—	ACS Reagent Chemicals
Iron (Fe)	≤0.001%	0.0002 %	—	Supplier specification
Sulfate (SO ₄)	≤0.01%	0.002 %	—	Supplier specification
Nitrogen compounds (as N)	≤0.001%	0.0001 %	ACS Reagent Chemicals — Nesslerization after alkaline distillation	Interpreted

Specification values are guaranteed limits. Typical values are representative of production lots and are not guaranteed. Lot-specific certificates of analysis ship with every order.

PHYSICAL & CHEMICAL PROPERTIES

PROPERTY	VALUE	SOURCE
Appearance	White crystals or granules; crystalline powder	Supplier specification
Form	Solid	Published reference
pH	11.5 – 12.5	Interpreted
Boiling Point	100	Published reference
Melting Point	Melting point equals 164 to 170 ° F	Published reference
Flash Point	N/A	Published reference
Solubility (water)	Soluble in water	Published reference

MATERIALS OF CONSTRUCTION

MATERIAL	RATING	MAX T (°C)	NOTES	SOURCE
Buna-N (NBR) Elastomer	Good	60	Acceptable	Cole-Parmer Chemical Compatibility
EPDM Elastomer	Excellent	100	Standard for brine gaskets.	Parker O-ring Chemical Compatibility
Viton (FKM) Elastomer	Excellent	100	Preferred elastomer	Cole-Parmer Chemical Compatibility
Borosilicate Glass Glass Ceramic	Excellent	100	Universally inert to salt solutions.	Cole-Parmer Chemical Compatibility
Concrete (sealed) Glass Ceramic	Good	—	Acceptable with epoxy coating	Cole-Parmer Chemical Compatibility

MATERIAL	RATING	MAX T (°C)	NOTES	SOURCE
304 stainless steel Metal	Fair	25	Pitting in chloride-rich service	Cole-Parmer Chemical Compatibility
316L Stainless Steel Metal	Good	60	Watch for chloride pitting above 60 °C in chloride salts.	NACE Chloride Pitting Guidelines
Aluminium Metal	Poor	—	Pitting; not recommended for brine	Cole-Parmer Chemical Compatibility
Carbon steel Metal	Poor	—	Rapid rust in brine	Cole-Parmer Chemical Compatibility
FRP Thermoplastic	Excellent	60	Common bulk-storage	Cole-Parmer Chemical Compatibility
HDPE Thermoplastic	Excellent	60	Universal salt brine compatibility.	Cole-Parmer Chemical Compatibility
PP Thermoplastic	Excellent	80	Acceptable for hot brine	Cole-Parmer Chemical Compatibility
PVC Thermoplastic	Excellent	60	Standard for brine piping.	Cole-Parmer Chemical Compatibility

Ratings reflect the service envelope (concentration × temperature) shown. Always confirm against your specific duty cycle and contact-time before equipment selection. The most cautious rating across overlapping references is shown.

REGULATORY & TRANSPORT

DOT / 49 CFR

UN NUMBER

Not regulated **Adjudicated**

PACKING GROUP

Not regulated **Adjudicated**

HAZARD CLASS

Not regulated **Adjudicated**

PROPER SHIPPING NAME

Not regulated **Adjudicated**

GHS / OSHA HAZCOM 2012

SIGNAL WORD

Warning **Adjudicated**

H-CODES (HAZARD STATEMENTS)

H314, H315, H319, H335 **Adjudicated**

P-CODES (PRECAUTIONARY STATEMENTS)

P260, P261, P264, P271, P280,

P301+P330+P331, P302+P352,

P303+P361+P353, P304+P340,

P305+P351+P338, P310, P314, P321,

P332+P313, P337+P313, P362, P363,

P403+P233, P405, P501

Adjudicated

OCCUPATIONAL EXPOSURE LIMITS

OSHA PEL (29 CFR 1910.1000)

— **no canonical**

ACGIH TLV

— **no canonical**

NIOSH REL

— **no canonical**

NIOSH IDLH

— **no canonical**

Transport descriptions reflect 49 CFR 172.101 lookup at time of publication. Sourced data: ECHA CLP Annex VI for harmonised classifications, NIOSH Pocket Guide for REL/IDLH, OSHA Z-Tables for PEL. Always verify against the latest regulatory text before shipment-critical decisions.

APPLICATIONS

Used in pharmaceuticals and as a buffering agent **jostchemical.com**

Pharmaceutical use and laboratory reagent use **jostchemical.com**

Reagent for testing USP/NF compendial monographs **labdepotinc.com**

Applications are drawn from published manufacturer and supplier documentation; each is sourced. Suitability for a specific use is the buyer's to confirm.

STORAGE & HANDLING

RECOMMENDED STORAGE

Store in a clean, dry warehouse in the original unopened containers.

jostchemical.com

INCOMPATIBILITIES

Specific incompatibilities depend on the salt — consult the SDS. Many salts react with strong acids to release gases.

Class-level guidance — not product-specific; the SDS controls.

For full hazard, PPE, and emergency response guidance, refer to the Safety Data Sheet (SDS) for this product. The SDS controls in all cases where guidance differs.

HANDLING PRECAUTIONS

Standard chemical PPE — dust mask and goggles for handling of fine grades. Avoid generating airborne dust.

Class-level guidance — not product-specific; the SDS controls.

SHELF LIFE

Consult Technical Services for product-specific shelf life

PACKAGING & LOGISTICS

SHIPPING DESCRIPTION (US DOT)

Not regulated for transport.

Confirm against shipping documents and carrier requirements before tender.

NMFC CLASS
70

REVISION HISTORY

Last reviewed 2026-07-17 by Andre Taki, DOT Hazmat Specialist.

VERSION	DATE	CHANGE	TRIGGER
1.2	2026-07-22	Canonical data updated: 2 fields changed via the provenance/adjudication pipeline. - ghsClassification · canonical change (coa.data_provenance / adjudication) - signalWord · canonical change (coa.data_provenance / adjudication)	canonical_change

VERSION	DATE	CHANGE	TRIGGER
1.1	2026-07-17	Canonical data re-verified: 6 fields updated against independent vendor SDSs, CLP Annex VI, 49 CFR, and OSHA HazCom 2024 (GHS classification, hazard/precautionary codes, signal word, physical properties as applicable). - countryOfOrigin · canonical adjudication / reground (coa.data_provenance) - dotSubsidiaryHazardClass · canonical adjudication / reground (coa.data_provenance) - ghsClassification · canonical adjudication / reground (coa.data_provenance) - hazard_h_codes · canonical adjudication / reground (coa.data_provenance) - hazard_p_codes · canonical adjudication / reground (coa.data_provenance) - hsCode · canonical adjudication / reground (coa.data_provenance)	canonical_change
1.0	2026-05-20	Initial URL-first TDS published from canonical chemistry registry.	initial

This Technical Data Sheet is provided for technical reference. The Safety Data Sheet (SDS) controls in all cases where guidance differs. Values reflect Alliance Chemical canonical data at time of generation; subsequent revisions are recorded in the Revision History above.